

EXHIBIT B

102 28957

XEROX

DATE

SUBJECT

hyperbranched PAE

PROJECT NO.

5



10

15

20

25

30



branched PAE

10 case 1: no t-butyl phenol. (500ml scale, compare
in case of 15.75g THPE
 depolymerization)

(A) 225g DMAc
 75g toluene
 38.73g BPA
 48.77g diCl-DPS
 63.33g $C_{52}Cl_{12}$
 7.88g THPE

20 (B) case 2: with t-butyl phenol. (1000ml scale, compare to
 15.75g THPE depolymerization
 and case A)

450g DMAc
 150g toluene
 77.45g BPA
 97.43g diCl-DPS
 140g $C_{52}Cl_{12}$
 15.75g THPE
 7.72g tBP
 + 29.55g diCl-DPS (additional to balance
 stoichiometry)

WITNESSED AND UNDERSTOOD

WORK AND RECORD

SIGNED

DATE

SIGNED

DATE

SIGNED

DATE

SIGNED

DATE